



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318  
(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)  
Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

---

---

We Identify and **S.T.O.P.** Your Noise Problems

**STORK**

Twin City Testing Corporation

PROJECT NUMBER: 18 0-0730.10

PAGE: 1 of 3

DATE: September 26, 2000

STOCK / TWIN CITY TESTING CORPORATION  
662 Cromwell Avenue  
St. Paul, Minnesota 55114

SOUND ABSORPTION TESTING CONDUCTED  
ON SIX BAFFLES CONSISTING  
OF 2" THICK PEPP

Prepared for:  
ACOUSTICAL SURFACES, INC

Attn: Mr. Steve Anderson  
123 Columbia Court North, Suite 201  
Chaska, MN 55318

Client Purchase Order Number 00012348

Test Conducted By:

Matthew N. Botz  
Project Engineer  
Product Testing Department  
(651) 659-7353

Reviewed By:

Richard O. Thomalla  
Acoustical Services Manager  
Product Testing Department  
(651) 659-7310

The test results contained in this report pertain only to the samples submitted for testing and not necessarily to all similar products.

An Affirmative Action



Equal Opportunity Employer





# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318  
(952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)  
Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

## We Identify and **S.T.O.P.** Your Noise Problems

**PROJECT NUMBER:** 18 0-0730.10

**PAGE:** 2 of 3

**DATE:** September 26, 2000

### SOUND ABSORPTION - ASTM C423-99a

#### INTRODUCTION:

This report presents the results of Sound Absorption testing conducted on six baffles consisting of a 2" thick PEPP material submitted by Acoustical Surfaces. This work was requested by Mr. Mike Nixon on September 6, 2000 with the testing conducted on September 14, 2000.

This report must not be reproduced except in its entirety with the approval of Stork / Twin City Testing Corporation. The data in this report relates only to the item tested.

Stork / Twin City Testing Corporation has been accredited by the U.S. Department of Commerce and the National Institute of Standards and Technology (NIST, formerly NBS) under their National Voluntary Laboratory Accreditation Program (NVLAP) for conducting this test procedure. This report may not be used to claim product endorsement by NVLAP or any agency of the U.S. Government.

#### TEST RESULTS SUMMARY:

The Sabins / Baffle average of the PEPP material was **5.55** at the NRC frequencies of 250, 500, 1000 and 2000 Hertz. A detailed data sheet is provided below under "TEST RESULTS".

#### TEST PROCEDURE:

ASTM: C423-99a, "Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method" was followed in every respect. The baffles were suspended above the floor of the reverberation chamber on cables. The full mounting and configuration details are provided under "TEST RESULTS" below.

#### TEST EQUIPMENT:

<u>Manufacturer</u>	<u>Model</u>	<u>Serial #</u>	<u>Description</u>
Norwegian Electronics	NE830	11511	Real Time Spectrum Analyzer
Brüel & Kjær	3923	815424	Rotating Microphone Boom
Larson-Davis	2560	1032	Pressure Condenser Microphone
Compaq Computer	V20 CIO	A942CZGZE580	Custom Designed Software

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document

- Soundproofing Products • Sonex™ Ceiling & Wall Panels • Sound Control Curtains • Equipment Enclosures • Acoustical Baffles & Banners • Solid Wood & Veneer Acoustical Ceiling & Wall Systems
- Professional Audio Acoustics • Vibration & Damping Control • Fire Retardant Acoustics • Hearing Protection • Moisture & Impact Resistant Products • Floor Impact Noise Reduction
- Sound Absorbers • Noise Barriers • Fabric Wrapped Wall Panels • Acoustical Foam (Egg Crate) • Acoustical Sealants & Adhesives • Outdoor Noise Control • Assistive Listening Devices
- OSHA, FDA, ADA Compliance • On-Site Acoustical Analysis • Acoustical Design & Consulting • Large Inventory • Fast Shipment • No Project too Large or Small • Major Credit Cards Accepted



# Acoustical Surfaces, Inc.

SOUNDPROOFING, ACOUSTICS, NOISE & VIBRATION CONTROL SPECIALISTS

123 Columbia Court North • Suite 201 • Chaska, MN 55318  
 (952) 448-5300 • Fax (952) 448-2613 • (800) 448-0121

Email: [sales@acousticalsurfaces.com](mailto:sales@acousticalsurfaces.com)  
 Visit our Website: [www.acousticalsurfaces.com](http://www.acousticalsurfaces.com)

## We Identify and **S.T.O.P.** Your Noise Problems

**PROJECT NUMBER:** 18 0-0730.10

**PAGE:** 3 of 3

**DATE:** September 26, 2000

**TEST RESULTS:**

Manufacturer : Acoustical Surfaces, Inc  
 Type : Baffles – 2" layer PEPP.  
 Dimensions (W x H x D) : 2' x 4' x 1"  
 Weight : 22 lbs. (0.46 psf)  
 Surface Area : 8.0 ft<sup>2</sup>  
 Total Surface Area : 96.0 ft<sup>2</sup> – consisting of 6 baffles – (2 sides)  
 Mounting Type : 3 specimens each, suspended on 2 cables – 16" between specimens – 41" from floor to specimens – 45" between cables

**Test No. 18 0-0730.10**

Frequency Hz	Absorption Coefficients)
100	1.95
125	1.17
160	1.36
200	1.97
250	2.53
315	2.69
400	3.42
500	3.67
630	3.87
800	4.71
1000	6.61
1250	8.66
1600	10.34
2000	9.39
2500	9.37
3150	10.92
4000	10.64
5000	11.11

**Sabins / Baffle Average (NRC Frequencies) = 5.55**

The NRC frequencies are at 250, 500, 1000, and 2000 Hz

G:\MMFILES\SKM\0730-10.ABS

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document